

- Part Bed Temperature: 178°C
- Feed Temperature: 135°C
- Piston/Cylinder Temperature: 165°C
- Layer Thickness: 0.1mm
- Energy Density: 0.21 J/mm<sup>3</sup>
- The SLS machine must maintain an inert environment during the printing process

